

EARTHENWARE versus STONEWARE

LOW FIRE CLAY BODY

Cone 04 (1945°F/1063°C) to Cone 06 (1826°F/998°C)

MID-RANGE


Cone 5 (2167° F/1186° C) to Cone 6 (2232° F/1222° C)

Low Fire


Mid-Range

Cone 010 09 08 07 **06 05 04** 03 02 01 1 2 3 4 **5 6** 7 8 9 10

Porous. Low fire clay bodies will absorb moisture.



The clay body becomes vitrified (glass like) and lacks porosity when fired to maturity.



Not recommended for dishwasher, microwave or oven as it's vulnerable to thermal shock.

Note: Hand washing is recommended.



May be used in the microwave, dishwasher and/or oven.

Note: Allow the ware to preheat with the oven to prevent thermal shock.




Treat like fine china or hand painted art.



An excellent choice for long-lasting and durable dinnerware surfaces.



Compatible with Mayco's Stroke & Coat®, Foundations®, Jungle Gems™ Crystal Glazes, Elements™, Fundamentals® and Specialty glazes.



Compatible with Stoneware glazes, Underglazes and Washes. Also compatible with many Mayco low fire glazes -i.e. Stroke & Coat®, Foundations®, Jungle Gems™ Crystal Glazes and many more. You can view mid-range color results at MaycoColors.com.

