


Technique was achieved by brushing on two (2) layers of base glaze (SW-171 Enchanted Forest). Then apply two (2) layers of top glaze, letting glazes dry between coats.






Vases shown are fired to Cone 6 on White Stoneware body.

Mayco"

MaycoColors.com



Technique was achieved by brushing on two (2) layers of base glaze (SW-171 Enchanted Forest). Then apply two (2) layers of top glaze, letting glazes dry between coats.





Vases shown are fired to Cone 10 reduction on White Stoneware body.

Mayco"

MaycoColors.com